



TEMPERATE HARDWOODS

CHERRY - AMERICAN

GRADE OVERVIEW:-

FAS, FAS/FAS IF, No.1 Common, No.2 Common.
Cherry is a species which can require sorting for colour such as 90/50 = 90% 1 face + 2 edges sap free, 50% reverse face sap free.

PROPERTIES

BOTANICAL NAME	Prunus serotina
DENSITY	580 kg/m ³
DISTRIBUTION	Occurs in the deciduous forest areas from Ontario to Florida and from the Dakotas to Texas, but only in small quantities or as scattered trees
DRYING	Relatively quick drying with some tendency to warp
DURABILITY	Moderately durable
ENVIRONMENTAL CREDENTIALS	FSC & FSC CW available
MOISTURE CONTENT	8 - 10% (+/-2%)
ORIGIN	North America
PHYSICAL/STRUCTURAL PROPERTIES	Hard with a fine straight close grain, Heartwood varies from reddish brown to rich red, SAP wood white to pinkish
PURCHASING CYCLE	12 month
STORAGE ADVICE	Under cover
TYPICAL APPLICATIONS	Furniture and cabinet making, high class joinery, kitchen cabinets, mouldings, panelling, flooring, doors, boat interiors, musical instruments, turning and carving
WORKING QUALITIES	Easy to machine, nails and glues well and when sanded, stained or polished produces excellent smooth finish. Dries quickly with moderately large shrinkage but is dimensionally stable after kilning



CHERRY - AMERICAN			
Product	Code	Stocked	Environmental Credentials
KD FAS/FAS1F 90/50			
1"	HSCRM025	Y	✓
1 X 8"+	H0002038	Y	✓
1.25"	HSCRM025	Y	✓
1.5"	HSCRM038	Y	✓
2"	HSCRM050	Y	✓
2 X 8"+	H0000905	Y	✓
2.5"	HSCRM063	Y	✓
3"	HSCRM075	Y	✓
4"	HSCRM100	Y	✓
KD FAS/FAS1F FSC 90/50			
1"	H0001244	Y	FSC
1.25"	H0004620	Y	FSC
1.5"	H0003381	Y	FSC
2"	H0003382	Y	FSC
2 X 9"+	H0006221	Y	FSC
3"	H0005395	Y	FSC
KD FAS/FAS1F Steamed			
1"	H0006300	Y	✓
1.25"	H0001759	Y	✓
2"	H0000178	Y	✓

Additional specifications, sizes, chain of custody and specials are available to order