



TEMPERATE HARDWOODS

MAPLE - AMERICAN HARD

GRADE OVERVIEW:-

FAS, FAS/FAS IF, No.1 Common, No.2 Common.
A further selection for colour with alternatives being: No.1 White, No.2 White, or mixture of both No.1 White & No.2 White.

PROPERTIES

BOTANICAL NAME	Acer saccharum
DENSITY	740 kg/m ³
DISTRIBUTION	Found generally in Canada and eastern USA
DRYING	All types dry without undue difficulty but rather slowly, particularly rock maple
DURABILITY	Slightly durable
ENVIRONMENTAL CREDENTIALS	FSC & FSC CW available
MOISTURE CONTENT	8 - 10% (+/-2%)
ORIGIN	North America
PHYSICAL/STRUCTURAL PROPERTIES	Compared with European beech, rock maple is about equal in bending strength and in compression along the grain and some 15 to 20% superior in hardness, resistance to shock loads and resistance to splitting
PURCHASING CYCLE	12 month
STORAGE ADVICE	Under cover
TYPICAL APPLICATIONS	Flooring, furniture, panelling, kitchen cabinets, worktops and table tops, interior joinery, stairs, handrails, mouldings and doors. The hardwearing properties and tight smooth grain make this species ideal for high traffic flooring applications such as theatres, concert halls, gymnasiums and basket ball courts
WORKING QUALITIES	Hard maple dries slowly with a large shrinkage so it can be susceptible to movement in performance. Pre boring is recommended when nailing and screwing. With care it maintains well, turns well. Glues satisfactorily and can be stained and polished to an outstanding finish

MAPLE - AMERICAN HARD			
Product	Code	Stocked	Environmental Credentials
KD FAS/FAS1F No.1&2 White			
1", 6' only	H0001995	Y	✓
1"	HSMWM025	Y	✓
1 x 8"+	H0000356	Y	✓
1.25"	HSMWM032	Y	✓
1.5"	HSMWM038	Y	✓
1.5 x 8"+	H0002009	Y	✓
2"	HSMWM050	Y	✓
2 x 8"+	H0000154	Y	✓
2.5"	HSMWM063	Y	✓
3"	HSMWM075	Y	✓
4"	HSMWM100	Y	✓
KD Hard Maple Glacial Select and Better White Sanded			
1"	H0004959	Y	✓
KD FAS/FAS1F No.1&2 White RTW (Ripped to width)			
1 x 3"	H0003062	Y	✓
1 x 4"	H0002934	Y	✓
1 x 5"	H0002935	Y	✓
1 x 6"	H0002936	Y	✓
KD Comsels			
1"	H0000091	Y	✓
2"	H0000243	Y	✓
KD FAS/FAS1F Brown			
1"	H0005912	Y	✓
KD FAS/FAS1F Hard Maple FSC No, 1&2 White			
1"	H0005604	Y	FSC
1.25"	H0005605	Y	FSC
1.5"	H0005606	Y	FSC
2"	H0005607	Y	FSC
KD FSC Comsels			
1"	H0004404	Y	FSC

Additional specifications, sizes, chain of custody and specials are available to order

