



# TEMPERATE HARDWOODS

## TULIPWOOD - AMERICAN (YELLOW POPLAR)

### GRADE OVERVIEW:-

FAS, FAS/FAS IF, No.1 Common, No.2 Common.

### PROPERTIES

<b>BOTANICAL NAME</b>	Liriodendron tulipifera
<b>DENSITY</b>	510 kg/m <sup>3</sup>
<b>DISTRIBUTION</b>	Eastern USA and Canada.
<b>DRYING</b>	Dries easily and well, with little degrade
<b>DURABILITY</b>	Slightly durable
<b>ENVIRONMENTAL CREDENTIALS</b>	FSC available
<b>MOISTURE CONTENT</b>	10% - 12% (+/-2%)
<b>ORIGIN</b>	North America
<b>PHYSICAL/STRUCTURAL PROPERTIES</b>	A medium density wood with low bending, shock resistance, stiffness and compression values. Very strong for its weight and ideal for laminating, beams and structures
<b>PURCHASING CYCLE</b>	12 month
<b>STORAGE ADVICE</b>	Under cover
<b>TYPICAL APPLICATIONS</b>	Construction, furniture, interior joinery, kitchen cabinets, doors, panelling, mouldings, turning and carving
<b>WORKING QUALITIES</b>	A versatile timber that is easy to machine, plane, turn, glue and bore. Dries easily with minimal degrade. Very good dimensional stability and little tendency to split when nailed. Takes and holds paint, enamel and stain exceptionally well

TULIPWOOD - YELLOW POPLAR			
Product	Code	Stocked	Environmental Credentials
<b>KD FAS/FAS1F</b>			
1"	HSPTM025	Y	✓
1 x 8"+	H0004861	Y	✓
1.25"	HSPTM032	Y	✓
1.5"	HSPTM038	Y	✓
1.5 x 8"+	H0004862	Y	✓
2"	HSPTM050	Y	✓
2.5"	HSPTM063	Y	✓
3"	HSPTM075	Y	✓
4"	HSPTM100	Y	✓
<b>KD FAS/FAS1F FSC</b>			
1"	H0004596	Y	FSC
1.25"	H0005393	Y	FSC
1.5"	H0004597	Y	FSC
2"	H0004034	Y	FSC
3"	H0005292	Y	FSC

Additional specifications, sizes, chain of custody and specials are available to order



Precise colour and texture should be judged from the actual material